

PS-020 Two Component Encapsulant

Description:

This product is a two-component silicone encapsulant, which is a liquid electronic material with various properties such as low density and buffering. The product can be cured at room temperature or under heat. It can be widely used to fill the gap between different electronic devices. It has excellent flowability and leveling before curing. After curing, it will not come out of the protective shell and can meet the wide range of customer needs.

Characteristic

- Good flowability and can effectively fill the gap
- Good insulation property with good reliability
- Good processability

Typical Applications

- LED lighting
- Automotive electronics
- Telecom base stations
- Microprocessors and graphic chips

Typi

vical Properties				
Properties	Typical value		Test method	
Before mix	Part A	Part B		
Color	Grey	White	Visual	
Viscosity* (mPa*s)	1,800	2,000	ASTM D2196	
Viscosity* (mPa*s)	2,100		ASTM D2196	
Density (g/cc)	0.7	0.7	ASTM D792	
Mix ratio	1:1		/	
Cured properties				
Color	Grey		Visual	
Durometer (Shore A)	30		ASTM D2240	
Dielectric Strength (kV/mm)	>10		ASTM D149	
Volume Resistivity $(\Omega^* cm)$	>10 ¹⁴		ASTM D257	
Working Time@25°C (h)	2		ASTM D2196	

BinMin Technology (Suzhou)Co. ,Ltd <u>http://www.baimin-tech.com/</u> TDS_PS-020 EN (Rev.01 03/21)





Properties	Typical value	Test method
Cure Time@25°C (h)	24	ASTM D2240
Cure Time@80°C (min)	30	ASTM D2240
Flame Classification	V-0	UL-94
Tensile Strength (MPa)	0.4	ASTM D412
Elongation (%)	20	ASTM D638
Operating Temperature (°C)	-40~150	1

*Brookfield DV2T HB-03, 20rpm

Storage:

- Shelf life: 6 months
- Temperature: 10°C~30°C
- Relative humidity: RH<70%

Package:

- 5kg/Kit (Part A and Part B 2.5kg each)
- 50kg/Kit (Part A and Part B 25kg each)

The technical data in this data sheet only represent typical values, not the test values of each batch of products. If you need the technical specification of the final product, please contact the relevant technical personnel.

All statements, technical information and recommendations provided by Baimin in this technical data sheet are all based on the products owned by the company after rigorous testing and evaluation. They have been compiled on the premise that they are trustworthy, but their correctness is not guaranteed. Please fully evaluate and decide for yourself whether the product meets your application requirements before you use our company's products. You need to take all the risks and responsibilities of your use.