



GF-600045 Thermal Conductive Gap Filler

Description:

This product is a two part silicone based thermally conductive gel, which is a paste-like material that can be cured at room temperature or elevated temperature. After curing, the product is a soft and compressible elastomer capable of dissipating heat between two different sources. The operating temperature of this product is from -40 to 200°C with excellent thermal performance and compliance, which can meet the customer needs.

Characteristic

- Good process ability and can effectively fill the gap
- Good insulation property with good reliability
- UL94 V-0 flame classification

Typical Applications

- LED lighting
- Automotive electronics
- Telecom base stations
- Microprocessors and graphic chips



Typical Properties

Properties	Typical value		Test method
Before mix	Part A	Part B	
Color	Blue	White	Visual
Viscosity* (mPa*s)	186,000	228,000	ASTM D2196
Viscosity* (mPa*s)	205,000		ASTM D2196
Density (g/cc)	3.45	3.45	ASTM D792
Mix ratio	1:1		/
Cured properties			
Color	Blue		Visual
Thermal Conductivity (W/m*K)	6.0		ASTM D5470
Durometer (Shore 00)	65		ASTM D2240
Dielectric Strength (kV/mm)	>8		ASTM D149
Volume Resistivity (Ω*cm)	>10 ¹²		ASTM D257



Properties	Typical value	Test method
Working Time@25°C (h)	2	ASTM D2196
Cure Time@25°C (h)	24	ASTM D2240
Cure Time@80°C (min)	30	ASTM D2240
Flame Classification	V-0	UL94
D3-D10 Content (ppm)	<50	ASTM F2466

*Brookfield DV2T SC4-14,25rpm

Application:

Part A and Part B should be thoroughly mixed 1:1 either by volume or weight and cured at room temperature or elevated temperature conditions. Static mixer is recommended for manual and automated mixing.

Storage:

- Shelf life: 6 months
- Temperature: 10°C~30°C
- Relative humidity: RH<70%

Package:

- 400mL dual cartridge
- 5 gallon pail
- 55 gallon drum

The technical data in this data sheet only represent typical values, not the test values of each batch of products. If you need the technical specification of the final product, please contact the relevant technical personnel.

All statements, technical information and recommendations provided by Baimin in this technical data sheet are all based on the products owned by the company after rigorous testing and evaluation. They have been compiled on the premise that they are trustworthy, but their correctness is not guaranteed. Please fully evaluate and decide for yourself whether the product meets your application requirements before you use our company's products. You need to take all the risks and responsibilities of your use.